

4. (Amended) The laminated extruded resin sheet comprising a methyl methacrylate resin according to Claim 1, wherein the insoluble methyl methacrylate resin particle is a methyl methacrylate resin particle having [high molecular weight] a weight-average molecular weight of 500,000 to 5,000,000 or a cross-linked methyl methacrylate resin particle.

Please cancel claims 3, 6 and 7 with neither prejudice nor disclaimer.

Please add new claims 9-15 as follows:

--9. The laminated extruded resin sheet according to Claim 1, wherein the base resin comprises 100 parts by weight of a methyl methacrylate resin and 5 to 70 parts by weight of a rubber-containing polymer.

10. The laminated extruded resin sheet according to Claim 1, wherein the base resin comprises 100 parts by weight of a methyl methacrylate resin and 5 to 50 parts by weight of a rubber-containing polymer.

11. The laminated extruded resin sheet according to Claim 1, wherein the resin layer (A) is made by dispersing uniformly 3 to 50 parts by weight of a rubber-containing polymer into 100 parts by weight of a methyl methacrylate resin, and the base resin comprises 100 parts by weight of a methyl methacrylate resin and 5 to 70 parts by weight of a rubber-containing polymer.

12. The laminated extruded resin sheet according to Claim 1, wherein the resin layer (A) is made by dispersing uniformly 3 to 20 parts by weight of a rubber-containing polymer into 100 parts by weight of a methyl methacrylate resin, and the base resin comprises 100 parts by weight of a methyl methacrylate resin and 5 to 50 parts by weight of a rubber-containing polymer.

13. The laminated extruded resin sheet according to Claim 9, 10, 11 or 12, wherein the rubber-containing polymer is an acrylic polymer comprised of a layer of an elastomer as an inner component and a hard layer as an outermost layer.

14. The laminated extruded resin sheet comprising a methyl methacrylate resin according to Claim 9, 10, 11 or 12, wherein the rubber-containing polymer is an acrylic polymer comprised of a hard layer as an innermost layer, a layer of an elastomer as an inner component and a hard layer as an outermost layer.

15. The laminated extruded resin sheet according to Claim 9, 10, 11 or 12, wherein the rubber-containing polymer is a graft copolymer obtained by graft-polymerizing 5